



Overview

Bringing brightness and a focus to cladding and feature walls.

A range of 11 two-tone primary and strong colour palates to make a bold statement. The Zest™ Collection uses polyester resin systems to achieve excellent exterior durability and gloss retention.

Zest finishes can be applied to aluminium, mild steel, galvanized steel and most metal substrates. When used in combination with chrome-free pre-treatment Zest gives a long-lasting & hard-wearing finish.

Approvals

Zest range includes powders of different properties defined by one or more of the approvals below.

Qualicoat: P-0301, P-0472, P-0560, P-0599.

Meets Qualicoat architectural powder coating specifications.

Properties

Applied gloss @ 60°: ISO2813. Tactile matt finish, 5% to 35% depending on finish chosen.

Applied film thickness: > 60 microns.

Finish: Rough texture.

Process

Pre-treatment:

Aluminium. Titanium-Zirconium (TiZr) non-chrome 6-stage pre-treatment.

Galvanized steel. Silane (Oxsilan) non-chrome 8-stage pre-treatment.

Powder application:

Corona discharge system.

Applied under ISO 9001: 2015 Quality Management System. Approval Nr: LRQ 4460, Certificate Nr 10532977

Key Points

- Excellent weather resistance
- Tactile finish
- Good edge coverage
- All powders are Qualicoat class 1
- Conforms to BS EN 12206-1
- Adaptable and flexible process
- Excellent visual detail even on small items

Test results

Zest component products and meet external architectural performance specifications.

Product specific data

Contract specific information

Project specific data

Contract specific information

Warranty

For C2 and C3 environments: 25-year warranty for gloss, colour and adhesion is offered as standard.

For C4 and C5I & C5M environments: Guarantees are conditional on project location, environmental conditions and pre-contract approval.

Warranties are offered in conjunction with Powdertech standard terms and conditions and a documented cleaning and maintenance programme.

Please note:

Whilst every care has been taken to provide accurate information this document is for guidance only and should be read in conjunction with other data sheets where applicable.

This document forms no part of a contract. Any warranty is subject to individual review.